


Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen



Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AA-6026	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSiBi T9	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
2,0	0,008		•							•	
2,5	0,013										
3,0	0,019	•	•			•			•		
4,0	0,034	•	•						•	•	
4,5	0,043		•				•				
5,0	0,053		•	•		•	•		•		
5,5	0,064		•								
6,0	0,076		•	•		•	•		•		
6,5	0,090		•								
7,0	0,104		•	•		•	•		•		
7,5	0,119		•								
8,0	0,136	•	•	•		•	•		•		
8,5	0,153		•								
9,0	0,172		•				•		•		
9,5	0,191		•								
10,0	0,212	•	•	•		•	•		•	•	•
11,0	0,256		•	•					•	•	

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AA-6026	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSiBi T9	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
12,0	0,31	•	•	•		•	•	•	•	•	
13,0	0,36		•	•			•	•	•	•	
13,5	0,39							•			
14,0	0,42		•	•		•	•	•	•	•	
14,5	0,45		•								
15,0	0,48	•	•	•		•	•	•	•	•	•
16,0	0,54	•	•	•		•	•	•	•	•	•
17,0	0,61		•	•		•		•		•	
18,0	0,69	•	•	•		•	•	•	•	•	•
19,0	0,77		•	•			•	•	•	•	
19,5	0,81							•			
20,0	0,85	•	•	•	•	•	•	•	•	•	•
21,0	0,93		•	•			•	•	•		•
21,5	0,98							•			
22,0	1,03	•	•	•		•	•	•	•	•	•
23,0	1,12		•	•			•	•		•	
24,0	1,22		•	•			•	•	•		

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AA-6026	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSiBi T9	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
25,0	1,32	•	•	•	•	•	•	•	•	•	•
26,0	1,43		•	•		•	•	•	•	•	
27,0	1,55		•	•			•	•			
28,0	1,66	•	•	•			•	•	•	•	
29,0	1,78		•	•				•			
30,0	1,91	•	•	•	•	•	•	•	•	•	•
31,0	2,04		•	•				•	•		
32,0	2,17	•	•	•		•	•	•	•	•	
33,0	2,31		•	•			•	•		•	
34,0	2,45		•	•			•	•		•	•
35,0	2,60	•	•	•	•	•	•	•	•	•	•
36,0	2,75	•	•	•			•	•	•		
37,0	2,90		•	•				•			
38,0	3,06		•	•		•	•	•	•		
39,0	3,22		•	•			•	•			
40,0	3,39	•	•	•	•	•	•	•	•	•	•
41,0	3,56		•	•							

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AA-6026	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSiBi T9	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
42,0	3,74		•	•			•	•	•	•	
43,0	3,92		•	•			•	•	•		
44,0	4,10		•	•							
45,0	4,29		•	•	•	•	•	•	•	•	•
46,0	4,48		•	•			•	•			
48,0	4,88		•	•			•	•			
50,0	5,30	•	•	•	•	•	•	•	•	•	•
51,0	5,51										
52,0	5,73		•	•			•	•	•		
55,0	6,41	•	•	•	•	•	•	•	•	•	•
56,0	6,65		•	•			•	•			
58,0	7,13							•			
60,0	7,63	•	•	•	•	•	•	•	•	•	•
61,0	7,89									•	
62,0	8,15		•	•				•			
63,0	8,41									•	
65,0	8,95	•	•	•	•	•	•	•	•	•	•

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AA-6026	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSiBi T9	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
70,0	10,4	•	•	•	•	•	•	•	•	•	•
72,0	11,0										
75,0	11,9		•		•	•	•	•	•	•	•
80,0	13,6	•	•		•	•	•	•	•	•	•
81,0	13,9									•	
82,0	14,3										
85,0	15,3	•	•		•	•	•	•		•	•
90,0	17,2	•	•	•	•	•	•	•	•	•	•
92,0	17,9										
95,0	19,1		•		•	•		•	•	•	
100,0	21,2	•	•	•	•	•	•	•	•	•	•
105,0	23,4		•		•		•	•	•	•	
110,0	25,6		•	•	•	•	•	•	•	•	•
115,0	28,0		•					•	•	•	•
120,0	30,5	•	•	•	•	•	•	•	•	•	•
125,0	33,1		•			•	•	•	•	•	•
130,0	35,8		•	•	•	•	•	•	•	•	•

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-1050A	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AW-6060	EN AW-6082	EN AW-7075
		Al99,5 H112	AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlMgSi T6 T66	AlSi1MgMn T6	AlZn5,5MgCu T6
135,0	38,6		•			•			•	
140,0	41,5	•	•	•	•	•	•	•	•	•
145,0	44,6		•						•	
150,0	47,7		•	•	•	•	•		•	•
155,0	50,9					•	•		•	
160,0	54,3	•	•		•	•	•		•	•
165,0	57,7		•						•	
170,0	61,3		•			•			•	•
172,0	62,7		•							
175,0	64,9									
180,0	68,7		•		•	•	•	•	•	•
185,0	72,5							•		
190,0	76,5		•		•		•		•	•
195,0	80,6									
200,0	84,8		•		•	•	•	•	•	•
205,0	89,1				•					
210,0	93,5		•		•	•	•		•	•

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-2007	EN AW-2011	EN AW-5083	EN AW-5754	EN AW-6012	EN AW-6082	EN AW-7075
		AlCu4PbMgMn T3 T4 T6	AlCu6BiPb T3 T8	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlSi1MgMn T6	AlZn5,5MgCu T6
215,0	98,0							
220,0	102,6	•			•	•	•	•
225,0	107,3							
230,0	112,1	•		•		•	•	•
235,0	117,0							
240,0	122,1	•			•		•	•
245,0	127,2							
250,0	132,5	•		•	•		•	•
255,0	137,8					•	•	
260,0	143,3	•		•	•		•	•
265,0	148,8			•				
270,0	154,5	•			•		•	•
275,0	160,3							
280,0	166,2	•		•	•		•	•
285,0	172,2							
290,0	178,2	•					•	•
295,0	184,4							

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-2007	EN AW-5083	EN AW-5754	EN AW-6012	EN AW-6082	EN AW-7075
		AlCu4PbMgMn T3 T4 T6	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlSi1MgMn T6	AlZn5,5MgCu T6
300,0	190,8	•	•	•		•	•
305,0	197,2						
310,0	203,7	•	•	•	•	•	•
315,0	210,3						
320,0	217,0	•	•	•		•	•
325,0	223,9						
330,0	230,8	•	•			•	•
335,0	237,9						
340,0	245,0	•					•
345,0	252,3						
350,0	259,6	•	•	•		•	•
355,0	267,1	•			•	•	
360,0	274,7	•	•			•	
365,0	282,4						
370,0	290,2	•	•			•	
375,0	298,1						
380,0	306,1	•	•			•	•

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen



Ø in mm	Kg/m ca.	EN AW-2007	EN AW-5083	EN AW-5754	EN AW-6012	EN AW-6082	EN AW-7075
		AlCu4PbMgMn T3 T4 T6	AlMg4,5Mn0,7 H112	AlMg3 H112	AlMgSiPb T6	AlSi1MgMn T6	AlZn5,5MgCu T6
385,0	314,2						
390,0	322,4	•					
395,0	330,7						
400,0	339,1	•	•			•	•
405,0	347,7						
410,0	356,3	•	•		•	•	
415,0	365,0						
420,0	373,9	•	•			•	
425,0	382,8						
430,0	391,9	•				•	
435,0	401,1						
440,0	410,3	•				•	
445,0	419,7						
450,0	429,2	•	•			•	•
455,0	438,8						
460,0	448,5	•	•			•	
465,0	458,3						

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen




Ø in mm	Kg/m ca.	EN AW-2007 AlCu4PbMgMn T3 T4 T6	EN AW-5083 AlMg4,5Mn0,7 H112	EN AW-6012 AlMgSiPb T6	EN AW-6082 AlSi1MgMn T6	EN AW-7075 AlZn5,5MgCu T6
470,0	468,2	•	•			
475,0	478,2					
480,0	488,3	•	•		•	
485,0	498,6					
490,0	508,9	•				
495,0	519,3					
500,0	529,9	•	•		•	
505,0	540,5					
510,0	551,3	•	•	•	•	
515,0	562,1					
520,0	573,1					
525,0	584,2					
530,0	595,4	•	•		•	
535,0	606,7					
540,0	618,0					
545,0	629,5					
550,0	641,1	•	•			

Rundstangen

Aluminiumlegierungen

gezogen · gepresst · gegossen



Ø in mm	Kg/m ca.	EN AW-2007 AlCu4PbMgMn T3 T4 T6	EN AW-5083 AlMg4,5Mn0,7 H112	EN AW-6082 AlSi1MgMn T6
560,0	664,7	•	•	•
580,0	713,0	•	•	•
590,0	737,8			•
600,0	763,0	•	•	
610,0	788,7	•		
630,0	841,2	•		
640,0	868,1		•	
650,0	895,5	•	•	
660,0	923,3		•	
700,0	1038,6		•	
750,0	1192,2		•	
800,0	1356,5		•	