

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CW453K CuSn8	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
26 / 14	3,35		•	•
26 / 17	2,70		•	
26 / 19	2,20		•	
29 / 19	3,35		•	
31 / 14	5,34		•	•
31 / 19	4,19		•	•
33 / 19	5,09		•	
33 / 23	3,91		•	
35,5 / 27,5	3,52	•		
36 / 14	7,69		•	•
36 / 19	6,53		•	•
36 / 24	5,03		•	•
36,5 / 22,5	5,77	•		
36,5 / 29,5	3,23	•		
37 / 17	7,55		•	
39 / 26	5,90		•	
39 / 28	5,15		•	
40,5 / 31	4,75	•		
41 / 14	10,37		•	•
41 / 19	9,22		•	•
41 / 24	7,72		•	•
41 / 29	5,87		•	•
42,5 / 34,5	4,30	•		
45,5 / 34	6,39	•		
46 / 14	13,41		•	•
46 / 19	12,26		•	•
46 / 24	10,76		•	•
46 / 29	8,91		•	•
46 / 34	6,71		•	•
48,5 / 37	6,87	•		
51 / 14	16,80		•	•
51 / 19	15,65		•	•
51 / 24	14,15		•	•
51 / 29	12,30		•	•
51 / 34	10,10		•	•
51 / 39	7,55		•	•
56 / 14	20,54			•
56 / 19	19,39		•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CW453K CuSn8	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
56 / 24	17,89		•	•
56 / 29	16,03		•	•
56 / 34	13,83		•	•
56 / 39	11,28		•	•
56 / 44	8,38		•	•
60,5 / 38	15,48	•		
61 / 19	23,47		•	•
61 / 24	21,97		•	•
61 / 29	20,12		•	•
61 / 34	17,92		•	•
61 / 39	15,37		•	•
61 / 44	12,47		•	•
61 / 49	9,22		•	•
65,5 / 54	9,60	•		
66 / 19	27,91		•	
66 / 24	26,41			•
66 / 29	24,56		•	•
66 / 34	22,36		•	•
66 / 39	19,81		•	•
66 / 44	16,91		•	•
66 / 49	13,66		•	•
66 / 54	10,06		•	
66,5 / 58	7,39	•		
71 / 18	32,96		•	•
71 / 23	31,52		•	•
71 / 28	29,74		•	•
71 / 33	27,61		•	
71 / 38	25,13		•	•
71 / 43	22,30		•	•
71 / 48	19,12		•	•
71 / 53	15,59		•	•
71 / 58	11,72		•	•
76 / 19	37,83			•
76 / 24	36,33		•	
76 / 28	34,88		•	•
76 / 33	32,75		•	•
76 / 38	30,27		•	•
76 / 43	27,44		•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
76 / 48	24,26	•	•
76 / 53	20,73	•	•
76 / 58	16,85	•	•
76 / 63	12,62	•	
82 / 28	41,50	•	•
82 / 33	39,37	•	
82 / 38	36,89	•	•
82 / 43	34,06	•	
82 / 48	30,88	•	•
82 / 53	27,35	•	•
82 / 58	23,47	•	•
82 / 63	19,25	•	•
82 / 68	14,67	•	•
87 / 28	47,40	•	
87 / 38	42,79	•	•
87 / 43	39,96	•	
87 / 48	36,78	•	•
87 / 53	33,26	•	•
87 / 58	29,38	•	•
87 / 63	25,15	•	•
87 / 68	20,58	•	•
87 / 73	15,65	•	
92 / 28	53,66	•	•
92 / 38	49,05	•	•
92 / 43	46,22		•
92 / 48	43,04	•	•
92 / 58	35,63	•	•
92 / 63	31,40	•	•
92 / 68	26,83	•	•
92 / 73	21,90	•	•
92 / 78	16,63	•	•
97 / 28	60,26	•	
97 / 38	55,65		•
97 / 43	52,82	•	
97 / 48	49,64	•	•
97 / 58	42,23	•	•
97 / 63	38,01	•	•
97 / 68	33,43	•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
97 / 73	28,50	•	•
97 / 78	23,23	•	•
97 / 83	17,61	•	
102 / 28	67,21	•	•
102 / 38	62,60	•	•
102 / 43	59,77	•	
102 / 48	56,59	•	•
102 / 58	49,18	•	•
102 / 68	40,38	•	•
102 / 73	35,46	•	•
102 / 78	30,18	•	•
102 / 83	24,56	•	
102 / 88	18,58	•	
107 / 43	67,07	•	
107 / 53	60,36	•	
107 / 63	52,26	•	
107 / 73	42,76	•	
107 / 78	37,48	•	
107 / 83	31,86	•	
107 / 88	25,88	•	
107 / 93	19,56	•	
112 / 28	82,16	•	
112 / 38	77,55	•	•
112 / 48	71,54	•	•
112 / 58	64,14	•	•
112 / 68	55,33	•	•
112 / 73	50,41	•	•
112 / 78	45,13	•	•
112 / 83	39,51	•	•
112 / 88	33,54	•	•
112 / 98	20,54	•	•
117 / 38	85,55	•	
117 / 53	76,01	•	•
117 / 63	67,91	•	
117 / 73	58,41	•	
117 / 83	47,51	•	•
117 / 88	41,53	•	
117 / 93	35,21	•	

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
117 / 98	28,54	•	•
117 / 103	21,52	•	
122 / 38	93,90	•	•
122 / 48	87,89	•	•
122 / 58	80,48	•	•
122 / 68	71,68	•	•
122 / 73	66,76	•	•
122 / 78	61,48	•	•
122 / 88	49,88	•	•
122 / 93	43,56	•	
122 / 98	36,89	•	•
122 / 103	29,87	•	
122 / 108	22,50	•	
127 / 43	99,77	•	
127 / 63	84,96	•	
127 / 73	75,45	•	•
127 / 78	70,18		•
127 / 83	64,56	•	•
127 / 93	52,26	•	
127 / 98	45,59	•	
127 / 103	38,57	•	
127 / 108	31,19	•	
132 / 48	105,64	•	•
132 / 58	98,23	•	•
132 / 68	89,43	•	•
132 / 78	79,23	•	•
132 / 88	67,63	•	•
132 / 98	54,63	•	•
132 / 108	40,24	•	•
132 / 118	24,45	•	
137 / 78	88,62		•
137 / 113	41,92	•	
142 / 58	117,37	•	•
142 / 68	108,57	•	•
142 / 78	98,37	•	•
142 / 88	86,77	•	•
142 / 98	73,78	•	•
142 / 108	59,39	•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
142 / 118	43,60	•	•
142 / 128	26,41	•	
152 / 48	145,32	•	•
152 / 58	137,91	•	•
152 / 68	129,11	•	•
152 / 78	118,91	•	•
152 / 88	107,31	•	•
152 / 98	94,32	•	•
152 / 108	79,93	•	•
152 / 118	64,14	•	•
152 / 128	46,95	•	•
157 / 123	66,51	•	
157 / 138	39,16	•	
162 / 58	159,85	•	
162 / 68	151,05	•	•
162 / 78	140,85	•	•
162 / 88	129,25	•	•
162 / 98	116,26	•	•
162 / 108	101,86	•	•
162 / 118	86,07	•	•
162 / 128	68,89	•	•
162 / 138	50,30	•	•
172 / 68	174,38	•	•
172 / 78	164,18	•	•
172 / 88	152,59	•	•
172 / 98	139,59	•	•
172 / 108	125,20	•	•
172 / 118	109,41	•	•
172 / 128	92,22	•	•
172 / 138	73,64	•	•
172 / 148	53,66	•	•
182 / 78	188,91		•
182 / 88	177,32	•	•
182 / 98	164,32	•	•
182 / 108	149,93	•	•
182 / 118	134,14	•	•
182 / 128	116,95	•	•
182 / 138	98,37	•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
182 / 148	78,39	•	•
182 / 158	57,01	•	
192 / 78	215,04	•	•
192 / 88	203,45	•	
192 / 98	190,45	•	•
192 / 108	176,06	•	•
192 / 128	143,08	•	•
192 / 138	124,50	•	•
192 / 148	104,52	•	•
192 / 158	83,14	•	•
192 / 168	60,36		•
202 / 73	247,85		•
202 / 78	242,57	•	
202 / 83	236,95		•
202 / 98	217,98	•	•
202 / 118	187,80	•	•
202 / 128	170,61	•	•
202 / 138	152,03	•	•
202 / 148	132,04	•	•
202 / 158	110,67	•	•
202 / 168	87,89	•	•
202 / 178	63,72	•	
212 / 108	232,51	•	•
212 / 118	216,72		•
212 / 128	199,53	•	•
212 / 138	180,95	•	•
212 / 148	160,97	•	•
212 / 158	139,59	•	•
212 / 168	116,81	•	•
212 / 178	92,64	•	•
222 / 82	297,35		•
222 / 88	290,22		•
222 / 98	277,22	•	•
222 / 118	247,04	•	•
222 / 128	229,86	•	
222 / 138	211,27	•	•
222 / 148	191,29	•	•
222 / 158	169,91	•	•

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
222 / 168	147,14	•	•
222 / 178	122,96	•	•
222 / 188	97,39	•	•
232 / 98	308,94	•	
232 / 118	278,76	•	•
232 / 138	242,99	•	•
232 / 148	223,01	•	•
232 / 158	201,63	•	
232 / 168	178,85	•	•
232 / 178	154,68	•	•
232 / 188	129,11	•	•
232 / 198	102,14	•	
242 / 88	355,05	•	
242 / 118	311,88	•	
242 / 138	276,11	•	•
242 / 148	256,13	•	•
242 / 158	234,75	•	•
242 / 168	211,97	•	
242 / 178	187,80	•	•
242 / 188	162,23	•	•
242 / 198	135,26	•	
252 / 98	376,57		•
252 / 128	329,20	•	•
252 / 148	290,64	•	•
252 / 158	269,26	•	
252 / 168	246,48	•	
252 / 178	222,31	•	•
252 / 188	196,74	•	•
252 / 198	169,77	•	•
252 / 208	141,41	•	
262 / 138	346,53	•	•
262 / 158	305,17	•	•
262 / 168	282,39	•	•
262 / 188	232,65	•	
262 / 198	205,68	•	•
262 / 208	177,32	•	
262 / 218	147,55	•	
272 / 138	383,84	•	

Rundrohre

Zinnbronze · Rotguss

gezogen · gepresst · Strangguss



AD / ID in mm	Kg/m ca.	CC493K CuSn7Zn4Pb7-C	CC483K CuSn12-C
272 / 168	319,70		•
272 / 198	242,99	•	
272 / 218	184,86	•	•
282 / 138	422,54	•	•
282 / 178	334,23	•	
282 / 198	281,70	•	•
282 / 218	223,57	•	
282 / 228	192,41	•	•
282 / 248	125,90	•	
292 / 198	321,80	•	
292 / 218	263,67	•	•
292 / 238	199,95	•	•
303 / 147	490,45	•	•
303 / 197	370,28	•	•
303 / 247	215,18	•	•
313 / 227	324,45		•
313 / 237	292,04	•	
322 / 268	222,59	•	
333 / 275	246,37		•
353 / 197	599,44	•	•
353 / 247	444,34	•	•
353 / 297	254,31	•	•